

Dry Slip Test Certificate

Thursday August 25th, 2016

Supplier: Floor Distributors (PO Box 197 Neutral Bay Junction, NSW 2089)

Sample Description: Balmain Oak

Date Tested: August 2016 (Tested through FORAY Laboratories – NATA Accreditation 1231)

Test Method: AS/NZS 4586-2004 Appendix B “Slip resistance classification of new pedestrian surface materials – Dry Floor Friction Test Method” using Slider 96

Test Data:

Sample Identification	Dry floor friction result ¹	Classification ² (Standards Australia Handbook 197)
Balmain Oak	0.47	D1

¹ Five test average value

² The classifications indicate that the contribution of the floor surfaces to the risk of slipping when dry is low



Dr. Vyt Garnys
PhD, BSc(Hons) AIMM, ARACI, ISIAQ
ACA, AIRAH, FMA
Managing Director and Principal Consultant



Nick Joy
BSc(Hons)
Consultant



Tuan Duong
B.Eng. (Chemical)
Consultant

CV160819